



紡織實驗室

Test Report

報告號碼: TX20465 /2013 /PL 日期: 2013 年 02 月 23 日 頁數: 二 之 二 頁

測試結果:

1. 耐磨強力 (依美國材料試驗協會 (12 kpa) (ASTM D4966-98(2007) Option 1-Martindale tester)

於 20,000 轉後

無斷紗

2. 潑水測試 (依美國紡織化學協會 AATCC 22:2010)

個別讀值 (原樣)

1.	100
2.	100
3.	100

等級: 100: 表面沒有濕潤
90: 表面稍有濕潤
80: 表面呈分散水滴狀之濕潤
70: 表面大部分有濕潤
50: 表面全部均有濕潤
0: 表面完全濕潤

3. 游離甲醛

測試方法: 參考中華民國國家標準 CNS 12943 L3234 第 5.3.1(2)節 方法 B, 使用紫外光/可見光分光光譜儀分析

測試結果
(ppm)

游離甲醛

未偵測出

備註: ppm = 百萬分之一
方法偵測極限值 5 ppm

由 SGS 相關實驗室執行

*** 結 束 ***

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested. This test report cannot be reproduced, except in full, without prior written permission of the Company. 除非另有說明, 此報告結果僅對測試之樣品負責。本報告未經本公司書面許可, 不可部份複製。

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at www.sgs.com/terms_and_conditions.htm and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.