

紡織實驗室

Test Report

報告號碼: TX82035/2012/PL

日期: 2012年 08月 30日

頁數:一之一頁

蘭陽精品家飾布

新北市板橋區國慶路49巷19弄9號

我們依照客戶的要求,根據客戶送交的樣品進行測試如下:

樣品敘述

一塊草綠色亞麻平織布

成

份

100% POLYESTER

原 產 地 台灣

收件日期

2012 年 08 月 28 日

測試週期

2012年08月28日至08月30日

測試項目 & 測試方法:

依申請者要求進行下列測試

測試結果:

潑水測試 (依美國紡織化學協會 AATCC 22:2010)

個別讀值 (原樣)

1.

100

2.

100

3.

100

等級: 100: 表面沒有濕潤

90: 表面稍有濕潤

80: 表面呈分散水滴狀之濕潤

70: 表面大部分有濕潤

50: 表面全部均有濕潤

0: 表面完全濕潤



Unless otherwise stated the results shown in this test report refer only to the sample(s) tested. This test report cannot be reproduced, except in full, without prior written permission of the Company. 除非另有說明,此報告結果僅對欄試之樣品負責。本報告未經本公司書面許可,不可部份複製。

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at www.sgs.com/terms and conditions.htm and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at www.sgs.com/en/Terms-and-Conditions/Terms-e-Document. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document to errorduced except in full, without prior written approval of the Company, and unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.